Product Specification: OmniCourt[®] Classic



Surface America, Inc. • PO Box 157 • Williamsville, NY 14231 Phone: (800) 999-0555 • Phone: (716) 632-8413 • Fax: (716) 632-8324 info@surfaceamerica.com • www.surfaceamerica.com

Part 1 - GENERAL

1.01 DESCRIPTION

A. OmniCourt Classic is a synthetic turf with sand infill; twisted polypropylene tape yarn.

1.02 QUALITY ASSURANCE

A. Manufacturer: APT Group, an ISO 9001 certified manufacturer, and distributed by Surface America Inc.

B. Face fibers shall be APT only; it shall be made of the highest quality resins and shall be mixed and extruded with specialized equipment designed for the manufacturing of artificial turf yarns, and stretched and annealed to the desired strength and durability required.

C. Urethane backing shall be a proprietary compound from APT, applied with state-of- the art equipment and properly oven cured to achieve the best tuft bind strength in the industry.

D. Turf manufacturer shall be vertically integrated, supplying all fibers, tufting, and backing at one location in the USA, having the capacity of producing 75,000,000 square feet annually.

Part 2 – PRODUCTS

Specifier Note: Contact: Surface America, PO Box 157, Williamsville, NY 14231; Telephone: (800) 999-0555, (716) 632-8413; Fax: (716) 632-8324; E-mail: <u>info@surfaceamerica.com</u>; website: <u>http://www.surfaceamerica.com</u>.

A. YARN

Yarn Type: Color Name: Total Denier: Thickness/Form: Total Yarn Face Weight:

APT FBPP10000-10-13PP Green Approx. 10,000 Approx. 100 micron twisted polypropylene tape 27oz./SqYd

B. BACKING

Primary Backing #1: Primary Backing #2: Primary Backing Weight: Secondary Coating: Total Product Weight: 13 pic polybac 13 pic polybac 7 oz./SqYd 20 oz. Urethane/SqYd 54 oz./SqYd C. TUFTING INFORMATION Pile Height: Stitch Rate: Tufting Gauge: Roll Widths: Drainage Perforations:

5/8" AS REQUIRED 3/8" 12' AVAILABLE

D. INFILL Sand: Size: Consumption:

Graded sub-angular silica sand 20 to 30 mesh 3.5 lbs. per square foot

Note: Lower sand content produces less foot slide and faster ball speed/lower bounce. Higher sand content increases foot slide and results in slower ball speed/higher bounce.

Test data may vary due to manufacturing tolerances or consumer specifications.